

Fireskin Foam 2.0

Two-Component Medium-Density Foam



PRODUCT DESCRIPTION

Fireskin Foam 2.0 is a two component, 1-1 parts by volume, medium density, spray applied polyurethane foam. To produce Fireskin Foam 2.0 requires the use of an A-Component (ISO) and a B-Component (RESIN), which contains zero ozone depleting blowing agents, catalyst, polyols and flame-retardant materials such as fiberglass, cellulose or other loose fill products. Typical areas where spray polyurethane foam is applied are interior walls, exterior walls, attics, ceilings and spa insulations.



HEALTH AND SAFETY

Read the Safety Data Sheet (SDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

Fireskin Foam 2.0 PHYSICAL PROPERTIES

R-Value	ASTM C518	6.5 @ 1"
Core Density	ASTM D1622	2.0 lbs./ft. ³
Closed Cell Content	ASTM D6226	>95%
Sound Transmission Coefficient	ASTM E413	37
Water Vapor Transmission - Permeance	ASTM E96	1.45 perms @ 1"
Air Impermeable	ASTM E283	1.5"-min. thick
Noise Reduction Coefficient	ASTM C423	0.10
Tensile Strength (psi)	ASTM D1623	51
Dimensional Stability	ASTM D2126	<0.27%
Compression Strength (psi)	ASTM D1621	41
Flame Spread	ASTM E84	Class I (20)
Smoke Development	ASTM E84	Class I (110)

TECHNICAL APPLICATION

Fireskin Foam 2.0 should be processed through commercially available, two-component, heated, spray equipment designed for that purpose. Primary heat and hose heat for spray equipment should both be set at 130°F with machine pressure at 1,500 psi. Fireskin Foam 2.0 should only be applied by a qualified professional applicator. It is the responsibility of the professional applicator to thoroughly understand all equipment, technical information and safe operating procedures that pertains to a spray polyurethane foam application.

WARRANTY

The information herein is believed to be reliable, but unknown risks may be present. Superskinsystems, Inc., warrants only that the materials shall be of merchantable quality. This warranty is in lieu of all other written or unwritten, expressed or implied warranties. Superskinsystems, Inc., expressly disclaims any warranty of fitness for a particular purpose, or freedom from patent infringement. Accordingly, buyer assumes all risks whatsoever as to the use of these materials. Buyer's exclusive remedy as to any breach of warranty or negligence claim shall be limited to the purchase price of the materials. Failure to strictly adhere to recommended procedures shall relieve Superskinsystems, Inc. of all liability with respect to the materials or the use thereof.

